

Thai PET Resin Co., Ltd.

MITSUI PET SE030T

One of the highest quality PET resins supplied by Thai PET Resin is SE030T. The basic chip physical properties of SE030T are listed below.

Items	Units	Typical Values	Methods
Basic Properties			
Intrinsic Viscosity	dl/g	0.80±0.05	Ubbelohde Viscometer
Density	kg/m ³	1,400	Density Gradient Tube
Thermal Properties			
Melting point	°C	247±2	Differential Scanning Calorimeter
Glass transition temperature	°C	80±2	Differential Scanning Calorimeter
Other Properties			
Color-L	-	75 min	Hunter Lab
Color-b	-	1 max	Hunter Lab
Acetaldehyde	ppm	1 max	Gas Chromatography (Head Space)
Bulk Density	kg/m ³	830	Gravimetric

Note : Figures shown here are typical values, not manufacturer's specifications.

Recommended Drying Temperature/Time : 160-170 °C and 4-7 hr.

Description

MITSUI PET SE030T is a medium intrinsic viscosity copolymer resin which is suitably designed for Sheet applications. For food applications, the resin is considered safe based upon compliance with the Japanese Ministry of Health, Labour and Welfare, Notification No.370, 1959.

The specialty resin offers good gas-barrier properties, and is tasteless and odorless, with high flavor retention and minimal flavor adsorption.

Warranty

Thai PET Resin warrants that its products will comply with the specifications and related regulatory compliance detailed in its publications. No other warranty, either expressed or implied regarding the suitability of the product for any particular purpose is made. The buyers are expected to make their own determination about the safety, health, environmental protection and suitability of use for their intended purposes. No warranty is made of the merchantability or fitness of any product and nothing herein waives any of the seller's conditions of sale.

Thai PET Resin Co., Ltd.

Bangkok Office: 1 Siam Cement Road, Building No.26, 2nd Floor, Bangsue, Bangkok 10800 Thailand
Tel. +66 2586 6408-13 Fax: +66 2586 6401

Rayong Office: 18 Prakornsongkroraj Road, Hemaraj Eastern Industrial Estate (Maptaphut), Soi G-2, Tambol Huay Pong, Muang District, Rayong 21150 Thailand
Tel. +66 3868 5900 Fax: +66 3868 5999
E-mail address : tprcmkt@cementthai.co.th